



## FBR 8950 12 PT BOARD


Designed to provide an economical product for general purpose bonding.

### FEATURES:

- Polyester carrier
- Excellent tack and adhesion
- High performance board liner

### BENEFITS:

- Excellent processing and die-cutting stability
- Suited for a broad range of general purpose applications



### CONSTRUCTION:

#### Unwind Adhesive:

Rubber Based

#### Carrier:

Polyester

#### Liner Adhesive:

Rubber Based

#### Liner:

12 Pt Natural Board

## FBR 8950 12 PT BOARD

Physical Properties	Typical Values	
	US Mils	MM's
THICKNESS		
Unwind Adhesive	2.0	0.05
Carrier	0.5	0.01
Liner Adhesive	1.5	0.04
Liner	12.4	0.31
Total	16.4	0.42

\*PSTC-133

### PEEL ADHESION

2 mil PET 180° 12" / min Initial

Substrate	Test Side	Lbf / in	US Oz / in	N / Meter
SS	Liner	9.5	153	1670
ABS	Liner	8.4	135	1474
PP	Liner	5.3	85	926
Talc PP	Liner	1.7	28	303
LDPE	Liner	4.0	64	706
HDPE	Liner	3.8	60	657
Painted Metal	Liner	6.9	8.2	1429

\*PSTC-101, ASTM D-3330, STD-10

### STATIC SHEAR

2 mil PET @ 72°F / 22°C 1" sq (6.5 cm<sup>2</sup>) 5.5 lbs (2.5 kg)

Substrate	Test Side	Min to Fail
SS	Liner	>1,200

\*PSTC-107, ASTM D-3654, STD-9

### TEMPERATURE

Min Application Temp	50°F	10°C
Max Continuous Operating Temp	150°F	66°C
Max Intermittent Operating Temp	175°F	79°C

\*TEST METHODS

Note: The listed values are typical only and not intended to serve as product specifications

### APPLICATION TECHNIQUES

- It is essential with all pressure-sensitive tapes the application surface is clean, dry and free of grease and oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (firm / rigid) surface achieves different performance

### STORAGE AND SHELF LIFE

The shelf life of the product is one year when stored at 18-22°C / 64-72°F, 30-70% relative humidity and out of direct sunlight, in original packaging.

Please refer to [Tapes.AveryDennison.com](http://Tapes.AveryDennison.com) for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2012 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. Avery™ and all other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Performance  
Tapes

Asia Pacific  
Kunshan, China,  
NO. 618 Nanhe Road  
Kunshan Economic &  
Technological Zone  
China, 215335  
Phone: +86 512 57155001  
Fax: +86 512 57155059

Europe  
Tieblokkenlaan 1  
B-2300 Turnhout  
Belgium  
Phone: +32 (0)14 40 48 11  
Fax: +32 (0)14 40 48 55

South America  
Rua Francisco Foga, 225  
13280-000 Vinhedo  
SP Brazil  
Phone: +55 19 3876 7736  
Fax: +55 19 3876 7682

North America  
250 Chester Street  
Painesville, Ohio  
44077 USA  
Phone: +1 866-462-8379  
Fax: +1 888-358-4469

For more information on our bonding tapes and adhesive solutions, visit [Tapes.AveryDennison.com](http://Tapes.AveryDennison.com)