



PATCO® 5410
**General Purpose Preservation
& Sealing Tape**


APPLICATIONS

- Long-term preservation, sealing, and splicing applications.
- Ideal for applications as a direct protective mask on aircraft, trucks, boats, and industrial equipment during outdoor storage.
- Used in conjunction with outdoor shrink film to secure film and seal film border during transport or extended outdoor use.

FEATURES & BENEFITS

- UV & weather resistant.
- Clean removal.
- Highly conformable.
- Will not break down after extended outdoor use.
- Resistant to staining and ghosting.
- Excellent low temperature adhesion.
- Adheres securely to contoured and irregular surfaces.
- Chemical and abrasion resistant.
- Applications requiring 30+ days of exposure should be fully tested and approved by the end user.

CONSTRUCTION



PRODUCT DESCRIPTION

Single-Coated Construction

Backing:

- Low Density Polyethylene

Adhesive:

- Rubber

Colors:

- White

TEST DATA

| Test | Typical Value | Typical Value (Metric) | Test Method |
|-------------------------------|----------------|---------------------------|-------------|
| Total Thickness | 9.0 mils | 0.229 mm | PSTC-133 |
| Substrate Thickness | 7.5 mils | 0.190 mm | PSTC-133 |
| Adhesion to Steel | 34 oz./in. | 0.372 N/mm | ASTM D-3330 |
| Tensile Strength | 17 lb./in. | 2.977 N/mm | ASTM D-3759 |
| Elongation (%) | 400 % | | |
| Application Temperature Range | 40°F to 120°F | 4°C to 49°C | |
| Operating Temperature Range | -40°F to 200°F | -40°C to 93°C | |

****Recommended storage conditions: 40-60% Humidity, 60 °F - 80 °F**

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.