

tesa® 62934

Double-sided PE-Foam Mounting Tape

tesa® 62934 is a double-sided PE-foam tape for constructive mounting applications. It consists of a highly conformable PE-foam backing and a tackified acrylic adhesive.

Product benefits:

- Versatile adhesive for high immediate adhesion on numerous substrates
- High ultimate adhesion level for a secure bonding performance
- UV, water and age resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorption

Main Application

- Decorative aluminium cover screens on brown goods
- Doorhandles in kitchen furniture
- Moulded plastic parts
- Mirrors and coloured glass panels

Technical Data

| | | | |
|--------------------|---------------------|-----------------------|----------------------|
| ▪ Backing material | PE foam | ▪ Type of adhesive | tackified acrylic |
| ▪ Color | black/white | ▪ Elongation at break | 250 % |
| ▪ Total thickness | 800 µm 31.5 mils | ▪ Tensile strength | 8 N/cm 4.6 lbs/in |

For latest information on this product please visit <http://l.tesa.com/?ip=62934>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

tesa® 62934

Double-sided PE-Foam Mounting Tape

Adhesion to

| | | | |
|-----------------------|--------------------------|-----------------------------|--------------------------|
| ▪ Steel (initial) | 17.0 N/cm 155.3 oz/in | ▪ Steel (after 14 days) | 17.0 N/cm 155.3 oz/in |
| ▪ ABS (initial) | 17.0 N/cm 155.3 oz/in | ▪ ABS (after 14 days) | 17.0 N/cm 155.3 oz/in |
| ▪ Aluminium (initial) | 17.0 N/cm 155.3 oz/in | ▪ aluminium (after 14 days) | 17.0 N/cm 155.3 oz/in |
| ▪ PC (initial) | 15.0 N/cm 137 oz/in | ▪ PC (after 14 days) | 17.0 N/cm 155.3 oz/in |
| ▪ PE (initial) | 2.7 N/cm 24.7 oz/in | ▪ PE (after 14 days) | 2.8 N/cm 25.6 oz/in |
| ▪ PET (initial) | 12.5 N/cm 114.2 oz/in | ▪ PET (after 14 days) | 17.0 N/cm 155.3 oz/in |
| ▪ PP (initial) | 2.8 N/cm 25.6 oz/in | ▪ PP (after 14 days) | 5.5 N/cm 50.2 oz/in |
| ▪ PS (initial) | 15.0 N/cm 137 oz/in | ▪ PS (after 14 days) | 17.0 N/cm 155.3 oz/in |
| ▪ PVC (initial) | 17.0 N/cm 155.3 oz/in | ▪ PVC (after 14 days) | 17.0 N/cm 155.3 oz/in |

Properties

| | | | |
|-------------------------------------|-----------------|--------------------------------------|---------|
| ▪ Temperature resistance short term | 80 °C 176 °F | ▪ Humidity resistance | ● ● ● ● |
| ▪ Temperature resistance long term | 80 °C 176 °F | ▪ Softener resistance | ● ● |
| ▪ Tack | ● ● ● | ▪ Static shear resistance at 73,4 °F | ● ● ● |
| ▪ Ageing resistance (UV) | ● ● ● | ▪ Static shear resistance at 104 °F | ● ● ● |

Evaluation across relevant tesa® assortment: ● ● ● ● very good ● ● ● good ● ● medium ● low

For latest information on this product please visit <http://l.tesa.com/?ip=62934>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

tesa® 62934

Double-sided PE-Foam Mounting Tape

Additional Information

Liner variants:

- PV0 brown glassine paper (71 µm)
- PV14 white PE-coated paper (120 µm)
- PV10 red MOPP (120 µm)
- PV15 blue PE (100µm)

tesa® 62934 has been tested by TÜV Rheinland, Germany. The test confirms the longterm adhesion performance after IEC 61215 / 61646 climate tests and a 85°C temperature resistance. (TÜV report number 21209595).

Peel Adhesion:

- immediate: foam splitting on Steel, Aluminium, ABS
- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC

For latest information on this product please visit <http://l.tesa.com/?ip=62934>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.