

## tesa® 62510

### Double sided PE foam mounting tape

tesa® 62510 is a double-sided PE-foam tape for mounting applications. It consists of a highly conformable PE-foam backing coated with a tackified acrylic adhesive.

#### Product benefits:

\*High ultimate adhesion level for a reliable bonding performance

\*UV, water and age resistant

- Suitable for outdoor applications
- \* Conformable PE foam core with high inner strength
- Suitable for automatic and manual module assembly

### Main Application

Muntin bar mounting

Solar module frames mounting

Trim and extruded profile mounting

General mounting applications

### Technical Data

▪ Backing material	PE foam	▪ Type of adhesive	tackified acrylic
▪ Color	black/white	▪ Elongation at break	180 %
▪ Total thickness	1000 µm 39.4 mils	▪ Tensile strength	10 N/cm 5.7 lbs/in

For latest information on this product please visit <http://l.tesa.com/?ip=62510>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

## tesa® 62510

### Double sided PE foam mounting tape

#### Adhesion to

▪ Steel (initial)	13.5 N/cm 123.3 oz/in	▪ Steel (after 14 days)	13.5 N/cm 123.3 oz/in
▪ ABS (initial)	8.0 N/cm 73.1 oz/in	▪ ABS (after 14 days)	13.5 N/cm 123.3 oz/in
▪ Aluminium (initial)	8.0 N/cm 73.1 oz/in	▪ aluminium (after 14 days)	13.5 N/cm 123.3 oz/in
▪ PC (initial)	8.0 N/cm 73.1 oz/in	▪ PC (after 14 days)	13.5 N/cm 123.3 oz/in
▪ PE (initial)	0.9 N/cm 8.2 oz/in	▪ PE (after 14 days)	0.9 N/cm 8.2 oz/in
▪ PET (initial)	6.0 N/cm 54.8 oz/in	▪ PET (after 14 days)	13.5 N/cm 123.3 oz/in
▪ PP (initial)	1.2 N/cm 11 oz/in	▪ PP (after 14 days)	1.2 N/cm 11 oz/in
▪ PS (initial)	8.0 N/cm 73.1 oz/in	▪ PS (after 14 days)	8.0 N/cm 73.1 oz/in
▪ PVC (initial)	13.5 N/cm 123.3 oz/in	▪ PVC (after 14 days)	13.5 N/cm 123.3 oz/in

#### Properties

▪ Temperature resistance short term	80 °C 176 °F	▪ Softener resistance	● ●
▪ Temperature resistance long term	80 °C 176 °F	▪ Static shear resistance at 73,4 °F	● ● ●
▪ Tack	● ● ●	▪ Static shear resistance at 104 °F	● ● ●
▪ Ageing resistance (UV)	● ● ● ●	▪ Static shear resistance at 158 °F	● ● ● ●
▪ Humidity resistance	● ● ● ●		

Evaluation across relevant tesa® assortment: ● ● ● ● very good ● ● ● good ● ● medium ● low

For latest information on this product please visit <http://l.tesa.com/?ip=62510>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

## tesa® 62510

Double sided PE foam mounting tape

### Additional Information

#### Liner variants:

PV0 brown glassine paper (2.75mils/70µm)

PV13 transparent PET (2mils/50µm)

PV15 blue PE (4mils/100µm)

#### Peel Adhesion:

-immediately: foam splitting on steel

-after 14 days: foam splitting on steel, ABS, Aluminum, PC, PET, PS, PVC

tesa® 62510 is recognized by UL as photovoltaic polymeric material (QIHE2).

tesa® 62510 has been tested by TÜV Rheinland, Germany. The test confirms the long-term adhesion performance after IEC 61215 climate tests and a 85°C temperature resistance.

The temperature resistance (short/long) of tesa® 62510 has been approved according to tesa test method under static load.

tesa® 62510 is certified by AAMA 813-11 for use as an adhesive used in Simulated Divide Lights.

For latest information on this product please visit <http://l.tesa.com/?ip=62510>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.