

CHR[®] 2283/2285

Extruded, Oriented, High Modulus PTFE Pressure Sensitive Adhesive Tape

CHR 2283 and 2285 are manufactured from extruded, oriented, high-modulus PTFE film coated with high-temperature pressure-sensitive adhesive.

Features/Benefits

The high-temperature resistance and anti-stick properties of PTFE make **CHR** 2283 and 2285 ideal products to be used as a release surface. Extremely durable and abrasion resistant, they will not curl or wrinkle making it long-wearing and easy to apply. They will not leave an adhesive residue when removed, resulting in less equipment down time.

Availability

Factory stock is in master rolls 33 m x 254 mm (36 yd x 10 in). Rolls can be slit in widths from 6.35 mm to 254 mm (0.25 in to 10 in). This material can also be supplied with a release liner if needed.

Applications

CHR 2283 and 2285 are ideal tapes for protecting extrusion and laminating equipment during the plastic extrusion coating process which combines plastic films with various substrates, most commonly paper. During this process, plastics are extruded onto the substrate as it passes between a neoprene roller and a cooling roller. **Saint-Gobain[®] CHR** 2283 and 2285 are used as a roller wrapping tape to protect the exposed ends of the neoprene roller from the molten plastic which is over-coated wider than the substrate.



CHR 2283/2285 Properties

Performance tests are run using standard test procedures.

The values presented are typical values and should not be used for specification purposes.

Product Number	2283-2	2285-2	2285-5
Backing Material	Film-PTFE	Film-PTFE	Film-PTFE
Adhesive Type	Acrylic	Silicone	Silicone
Total Thickness mm (mil)	0.102 (4.0)	0.089 (3.5)	0.165 (6.5)
Backing Thickness mm (mil)	0.051 (2.0)	0.051 (2.0)	0.127 (5.0)
Adhesive Thickness mm (mil)	0.051 (2.0)	0.038 (1.5)	0.038 (1.5)
Adhesion to Steel N/cm (oz/in)	3.3 (30)	3.3 (30)	4.4 (40)
Tensile Strength N/cm (lb/in)	53 (30)	53 (30)	131 (75)
Dielectric Strength (volts)	10,000	9,000	16,000
Elongation (% at break)	150	175	200
Operating Temperature °C (°F)	-40 to +177 (-40 to +350)	-73 to +260 (-100 to +500)	-73 to +260 (-100 to +500)
Color	Rust	Rust	Rust



Performance Plastics - Tape Solutions

North America | South America | Europe | Asia

For a full list of locations, please visit
tapesolutions.saint-gobain.com/contact-us

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain Performance Plastics assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: For a period of 6 months, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Form #1153 | © Saint-Gobain March 2018 | **CHR**, **CHRTape** and **Saint-Gobain** are trademarks of Saint-Gobain.