



CHR® C/2355

FEP Pressure Sensitive Adhesive Tape

CHR C and 2355-2 are manufactured from clear FEP (fluorinated ethylene propylene) film with pressure-sensitive, high-temperature silicone adhesive.

Features/Benefits

Both **CHR C** and 2355-2 tapes are very durable and versatile products. The FEP backing offers excellent high temperature resistance and they offer the highest electrical strength in volts per mm. FEP backing is chemically inert, thin and conformable. The tape construction is weather resistant, stable and non-toxic.



Availability

Factory stock for both tapes is in master log form 33 m x 635 mm (36 yd x 25 in) wide. Rolls can be slit 12.7 mm to 635 mm (0.5 in to 25 in) wide. Slit rolls under 12.7 mm (0.5 in) wide are available in 16.5 m (18 yd) long rolls only. They are available with or without a liner.

Applications

CHR C and 2355-2 tapes are often used for coil and transformer insulation. Due to its transparency, these tapes are useful for “see through” identification on wire harnesses.

CHR C/2355 Properties

Performance tests are run using standard test procedures.

The values presented are typical values and should not be used for specification purposes.

Product Number	C	2355-2
Backing Material	Film-FEP	Film-FEP
Adhesive Type	Silicone	Silicone
Total Thickness mm (mil)	0.089 (3.5)	0.089 (3.5)
Backing Thickness mm (mil)	0.051 (2.0)	0.051 (2.0)
Adhesive Thickness mm (mil)	0.038 (1.5)	0.038 (1.5)
Adhesion to Steel N/cm (oz/in)	2.2 (20)	2.2 (20)
Tensile Strength N/cm (lb/in)	14 (8)	14 (8)
Elongation (% at break)	275	275
Dielectric Strength (volts)	9,000	9,000
Direct Electrolytic Corr.	1.0	1.0
Operating Temperature °C (°F)	-73 to +204 (-100 to +400)	-73 to +204 (-100 to +400)
Colour	Clear	Clear

**Performance Plastics - Tape Solutions**

North America | South America | Europe | Asia

For a full list of locations, please visit
tapesolutions.saint-gobain.com/contact-us

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain Performance Plastics assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: For a period of 6 months, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Form #1129 | © Saint-Gobain March 2018 | **CHR** and **CHRTape** are trademarks of Saint-Gobain.