

# PE8

## PRESERVATION TAPE

### DESCRIPTION

PE8 has a durable, moisture resistant PE (polyethylene) backing with a rubber-based pressure-sensitive adhesive. Bonds well to a variety of surfaces. Clean removal from a variety of gel-coated surfaces.

Designed to offer a high degree of conformability without excessive stretch. Stiffer backing makes it easier to handle in certain applications. UV resistance up to six (6) months, depending upon conditions and surfaces.

### PRODUCT APPLICATION

For patching and repairs, bundling and wrapping applications, sealing, and separation of dissimilar metals, color coding and identification. Can be used for seaming or sealing PE films used for marine and transportation preservation.

### SPECIFICATION CONFORMANCE

Tested in accordance with UL723 / ASTM E84



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA  
Customer Service: 800.IPG.8273 | 800.474.8273  
Tape Technical Service: 877.447.4832  
[www.itape.com](http://www.itape.com) | [info@itape.com](mailto:info@itape.com)

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 06/18

## INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

### NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

<b>Backing</b>	Polyethylene (PE) Film
<b>Adhesive</b>	Synthetic Rubber
<b>Adhesion to Steel</b> (oz/in of width) ASTM D3330	75 (20.5) N/25mm
<b>Tensile Strength</b> (lbs./in of width) ASTM D3759	18 (78.8) N/25mm
<b>Total Thickness</b> (mils) ASTM D3652	9.0 (0.23mm)
<b>Application Temperature Range</b>	+45°F to +120°F (+7°C ~ +49°C)
<b>Operating Temperature Range</b>	+20°F ~ +150°F (-7°C ~ +65°C)
<b>Color</b>	White

