

FBL100

FILM/FOIL LAMINATE BARRIER SPECIALTY MATERIAL

DESCRIPTION

The conformability and flexibility of polypropylene and LDPE films provide superior sealing, protective benefits, and ease of handling characteristics of a high quality product. Resistant to water, paint stripping chemicals, oils and grease. Designed and engineered for use during chemical (paint) stripping of aircraft to provide vapor barrier and UV protection. Provides superior WVTR properties and chemical resistance.

PRODUCT APPLICATION

Surface protection of sensitive areas of aircraft and parts.

GOVERNMENT COMPLIANCE

Conforms to specification MIL-PRF-131K, Class 1 (pending) for heat sealable military spec. packaging of perishable materials.



intertape polymer group™

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA

Customer Service: 800.IPG.8273 | 800.474.8273

Tape Technical Service: 877.447.4832

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 11/13

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

PHYSICAL PROPERTIES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing (laminate)	BOPP/Aluminum Foil/ LDPE
Tensile Strength (lbs/in width)	50 (min)
Puncture Resistance (lbs)	15 (min)
Total Thickness (mils)	4.8
Resistance to Curl	5% (max)
Blocking Resistance	No blocking, delamination or rupture
Contact Corrosivity	No corrosion, etching or pitting
Oil/Chemical Resistance	No leakage, swelling, delamination or embrittlement
Water Vapor Transmission Rate	0.02 (max) room temperature
Color	'Metalized' Silver

