

ALF150L

UTILITY ALUMINUM FOIL TAPE WITH LINER

DESCRIPTION

A general purpose aluminum foil tape with high tack pressure-sensitive rubber based adhesive. For seaming and sealing fiberglass duct board and duct wrap to enhance appearance and maintain vapor barrier integrity. Recommended minimum application temperature 40°F (4°C). The shiny aluminum backing offers excellent reflective properties (i.e. heat, light). Poly-coated (43#) / 3.3 mil PCK liner.

PRODUCT APPLICATIONS

HVAC (Heating, Ventilation and Air Conditioning) applications. For use also in Industrial, Appliance, Marine and Aerospace industries.

GOVERNMENT COMPLIANCE

Test in accordance with ASTM E-84 / UL-723



intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA

Customer Service: 800.IPG.8273 | 800.474.8273

Tape Technical Service: 877.447.4832

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 12/17

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing ASTM C-1136	1.5 mil (38μ) Aluminum Foil
Adhesive	Synthetic Rubber / Resin
Tensile Strength (lbs/in width) ASTM D-3759	18 (79 N/25mm)
Elongation (% at break) ASTM D-3759	3
Adhesion to Steel (oz./in. width) ASTM D-3330	93 (25.5 N/25mm)
Total Thickness w/o liner (mil) ASTM D-3652	3.3 (0.083 mm)
Flame Spread ASTM E-84 / UL-723	≤ 25
Smoke Developed ASTM E-84 / UL-723	≤ 50
Operating Temperature Range	0°F ~ +200°F -17°C ~ +93°C

