

# ALF Mastic Foil Tape

## SPECIALTY BUTYL MASTIC FOIL TAPE

### DESCRIPTION

High tack, low VOC 17 mil aluminum 'mastic' foil tape coated with a pressure-sensitive, modified butyl rubber adhesive. Provides an instant waterproof grip to a variety of surfaces and a full bond in 24 hours. Features a release liner for ease of use and has excellent flexibility with no cracking. ALF Mastic is a LEED points contributor. Highly resistant to the effects of weather, UV, temperature, mold and mildew. Paintable.

### PRODUCT APPLICATION

Excellent for use on sheet metal, duct board, flex duct, PVC coated duct, and duct wrap vapor barriers. Ideal for replacement applications and other general purpose duct joint and HVAC applications.

### GOVERNMENT COMPLIANCE

Tested in accordance with UL-723  
Seal Class A  
VOC Limitations SCAQMD Rule 1168  
City of Los Angeles Approval RR#8069



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA

Customer Service: 800.IPG.8273 | 800.474.8273

Tape Technical Service: 877.447.4832

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 2/15

## INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

### NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

<b>Adhesive</b>	Modified Butyl Rubber
<b>Backing</b>	Aluminum
<b>Peel Strength</b>	>10 lbs / linear inch
<b>Tensile Strength</b>	955 psi
<b>Service Temperature</b>	-20°F to +180°F (-28.9°C to +82°C)
<b>Application Temperature</b>	+35°F to +110°F (-1.7°C to +43°C)
<b>Flame Spread</b>	20
<b>Smoke Developed</b>	40
<b>Total Thickness (mils)</b>	17 (0.43mm)
<b>Color</b>	Metallic

