

DCT090A

UTILITY GRADE DOUBLE-COATED TISSUE TAPE

DESCRIPTION

Non-woven tissue paper coated on both sides with an aggressive, pressure-sensitive, solvent acrylic adhesive. Provides excellent adhesion to a variety of surfaces as well as excellent resistance to oils, some plasticizers, ultraviolet light (UV) and higher temperatures than rubber based adhesives.

PRODUCT APPLICATION

Designed for high performance splicing in a continuous web processes, ideal for use with corrugated paper. Used for bonding and laminating of a range of cloths, vinyl's, rigid and flexible plastic as well as lamination in the leather industry. Also great for mounting of signs, covers, posters, name plates and it is used in the automotive industry for the mounting of door linings.



intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA

Customer Service: 800.IPG.8273 | 800.474.8273

Tape Technical Service: 877.447.4832

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 05/14

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing	Tissue
Adhesive	Solvent Acrylic
Adhesion to Steel (oz/in) PSTC-101	45 (12.3 N/25mm)
Elongation (% at break) ASTM D3759	3.5
Service Temperature Range	-4°F to 212°F (-20°C to 100°C)
Application Temperature	50°F to 104°F (10°C to 40°C)
Total Thickness w/o Liner (mils) PSTC-133	4.3 (0.11mm)
Liner	White SCK

