

CHR® A2005

PTFE-Glass Pressure Sensitive Adhesive Tape

CHR A2005 is fibreglass fabric impregnated with PTFE dispersion and coated with high-temperature, pressure-sensitive silicone adhesive.

Features/Benefits

CHR A2005 is a very durable and versatile product. The combination of PTFE, fibreglass and a high temperature silicone adhesive allows A2005 to perform in continuous temperatures up to 260°C (500°F). A2005 is dimensionally stable and resistant to tears, punctures, abrasion and wear. It will not “cold flow” under heavy loads.

Availability

CHR A2005 is available in widths from 6.35 mm to 991 mm (0.25 in to 39 in) wide. Standard roll length is 16.5 m or 33 m (18 yd or 36 yd). **CHR A2005** is available with or without a liner.

Applications

CHR A2005 is frequently used by the packaging industry as a release surface on heat sealers, blister formation and form-fill-seal equipment. The durability and anti-stick properties of **CHR A2005** also make it an ideal material for the lining of guide rails, chutes and slides. The high temperature capabilities and non-stick properties of **CHR A2005** allow it to perform as an excellent release surface in the composite aircraft industry.



CHR A2005 Properties

Performance tests are run using standard test procedures.

The values presented are typical values and should not be used for specification purposes.

Product Number	A2005
Backing Material	PTFE-Coated Fibreglass Fabric
Adhesive Type	Silicone
Total Thickness mm (mil)	0.140 (5.5)
Backing Thickness mm (mil)	0.076 (3.0)
Adhesive Thickness mm (mil)	0.064 (2.5)
Adhesion to Steel N/cm (oz/in)	5.5 (50)
Tensile Strength N/cm (lb/in)	158 (90)
Elongation (% at break)	<5
Operating Temperature °C (°F)	-73 to +260 (-100 to +500)
Colour	Natural

**Saint-Gobain Tape Solutions**

North America | South America | Europe | Asia

For a full list of locations, please visit
[tapesolutions.saint-gobain.com/contact-us](https://www.tapesolutions.saint-gobain.com/contact-us)

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: For a period of 6 months, Saint-Gobain warrants this product(s) to be free from defects in manufacturing. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Form #1131 | © Saint-Gobain July 2020 | **CHR** and **CHRTape** are trademarks of Saint-Gobain.