

tesa® 4967

Double-sided extra strong filmic tape

PRODUCT INFORMATION

Product Description

tesa® 4967 is a transparent double-sided self-adhesive tape consisting of a PET backing and a modified acrylic adhesive.

tesa® 4967 features especially:

- Extremely high holding power even at elevated temperatures
- Superior converting performance due to strong PET backing and reduced adhesive mass flow
- Good bonding performance even to LSE materials

Main Application

- Mounting lenses to mobile phone housings
- Mounting of ABS plastic parts in the automotive industry
- Mounting of decorative profiles and mouldings in the furniture industry

Technical Data

■ Backing material	PET film	■ Type of adhesive	tackified acrylic
■ Color	transparent	■ Elongation at break	50 %
■ Total thickness	160 µm 6.3 mils	■ Tensile strength	20 N/cm 11.4 lbs/in

Adhesion to

■ Steel (initial)	11.3 N/cm 103.2 oz/in	■ Steel (after 14 days)	13.4 N/cm 122.4 oz/in
■ ABS (initial)	9.8 N/cm 89.5 oz/in	■ ABS (after 14 days)	10.8 N/cm 98.7 oz/in
■ Aluminium (initial)	9.6 N/cm 87.7 oz/in	■ Aluminium (after 14 days)	12.2 N/cm 111.5 oz/in
■ PC (initial)	11.7 N/cm 106.9 oz/in	■ PC (after 14 days)	13.1 N/cm 119.7 oz/in
■ PE (initial)	5.2 N/cm 47.5 oz/in	■ PE (after 14 days)	5.7 N/cm 52.1 oz/in
■ PET (initial)	9.3 N/cm 85 oz/in	■ PET (after 14 days)	10.5 N/cm 95.9 oz/in
■ PP (initial)	5.3 N/cm 48.4 oz/in	■ PP (after 14 days)	7.0 N/cm 64 oz/in
■ PS (initial)	10.2 N/cm 93.2 oz/in	■ PS (after 14 days)	11.1 N/cm 101.4 oz/in
■ PVC (initial)	8.9 N/cm 81.3 oz/in	■ PVC (after 14 days)	11.9 N/cm 108.7 oz/in

tesa tape, inc.

5825 Carnegie Boulevard
Charlotte, NC 28209
Phone: 704 554 0707
Toll Free: 800 426 2181
Fax: 800 852 8831
customer@tesatape.com

Technical Tape México S.A. de C.V.

Av. Santa Fe No. 170
German Centre P 6-3-3Col.
Lomas de Santa Fe
Mexico D.F. C.P. 01210
Phone: +52 (55) 5292 6978
Fax: +52 (55) 5292 6977

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to advise you.

tesa® 4967

Double-sided extra strong filmic tape

PRODUCT INFORMATION

Properties

■ Static shear resistance at 73,4°F	+	■ Humidity resistance	++
■ Static shear resistance at 104°F	+	■ Temperature resistance short term	200 °C
■ Tack	+		392 °F
■ Resistance to chemicals	+	■ Temperature resistance long term	100 °C
■ Ageing resistance (UV)	++		212 °F
		■ Softener resistance	+

Evaluation across relevant tesa® assortment: ++ very good, + good, o medium, - low

Additional Info

Liner variants:
 PV0 brown glassine paper (71µm; 82g/m²)
 PV6 red MOPP-film (80µm; 72g/m²)
 PV7 transparent PET-film (50µm; 72g/m²)
 PV16 white MOPP-film (80µm, 72g/m²)

Page 2 of 2 / As of 05/20/10

tesa tape, inc.

5825 Carnegie Boulevard
 Charlotte, NC 28209
 Phone: 704 554 0707
 Toll Free: 800 426 2181
 Fax: 800 852 8831
 customercare@tesatape.com

Technical Tape México S.A. de C.V.

Av. Santa Fe No. 170
 German Centre P 6-3-3Col.
 Lomas de Santa Fe
 Mexico D.F. C.P. 01210
 Phone: +52 (55) 5292 6978
 Fax: +52 (55) 5292 6977