




## Premium UL181A& B-FX Foil Tape



- Backing:** Printed 2 mil Foil
- Adhesive:** Cold weather Acrylic
- Liner:** Unbleached Natural Kraft Paper
- Colors:** Aluminum
- Specifications:** UL181A & UL181B-FX Listed
- Standard Sizes:** 2.5" x 60Yd, 72mm x 55m

### Applications

- Permanently seals seams in fiberglass duct board and flexible ducts for HVAC systems
- Suitable for use on rigid sheet metal ducts
- Durable seal for dryer ventilation

### Features & Benefits

- Aggressive cold weather acrylic adhesive
- Superior performance in all climate conditions
- Mold & Mildew Resistant
- New unbleached kraft release liner
- Reduced environmental impact
- UL181A & B-FX Listed
- Meets code requirements and can contribute toward requirements for EA Credit 1 (Optimize Energy Performance) under LEED®
- Low VOC Content
- Can contribute toward satisfying EQ Credit 4.1 (Low Emitting Materials) under LEED®

### Physical Properties

	Standard UOM	Metric UOM	Test Method
<b>Total Thickness</b>	4.8 mils	121.92 mic	ASTM D-1000
<b>Adhesion to Steel</b>	68 oz/in	7.44 N/cm	PSTC-101
<b>Adhesion to Backing</b>	60 oz/in	6.57 N/cm	PSTC-101
<b>Tensile Strength</b>	27 lb/in	47.28 N/cm	ASTM D-1000
<b>Operating Temperature</b>	-20 to 325° F	-29 to 163°C	
<b>Application Temperature</b>	-10 to 200° F	4 to 93° C	
<b>Flame Spread</b>	3		
<b>Smoke Developed</b>	0		
<b>VOC Content</b>	<30 g/L		

Recommended Storage Conditions: 40-60% Humidity, 60°F - 80°F  
 Standard Shelf Life (at 25C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.