

**No Skidding®**



266 Wildcat Rd, Toronto, ON M3J 2N5 Canada  
Phone: (416) 667-1788 Fax: (416) 667-1783  
sales@noskidding.com www.noskidding.com  
or call us Toll Free at 1-800-375-0571

# NS 5600B SERIES

## ANTI SLIP SAFETY TAPE

### MOP FRIENDLY BLACK GRIT TAPE

## No Skidding Anti Slip Safety Mop Friendly Black Grit Tape NS5600B

### DESCRIPTION

No Skidding® Mop Friendly Black Grit Tape is a commercial grade aluminum oxide non-slip tape that has been designed to meet OSHA standards for general-purpose anti-slip surface applications.

### APPLICATIONS

No Skidding® Mop Friendly Black Grit Tape is designed for indoor and outdoor non-skid applications that require long-term anchorage to a variety of surfaces. It has been successfully used in a wide range of markets including OEM, Actions Sports and Building Safety. It is certified for "High Traction".



Sizes: 1", 2", 3", 4", 6", 12" X 60 ft. Also 6" X 24", 50 pieces / case. We can customize cleat sizes per your specifications.

### PROPERTIES

PHYSICAL PROPERTIES	TEST METHODS	TYPICAL RESULTS
Thickness	PSTC – 133 - Substrate - Pressure Sensitive adhesive - Release Liner	0.044 inch (1.120 mm) 0.002 inch (0.051 mm) 0.006 inch (0.152 mm)
Peel Adhesion To:	PSTC – 101	
- Stainless Steel	15 minute dwell 24 hour dwell	68 oz/in (75 N/100 mm) 100 oz/in (110 N/100 mm)
- Powder Coated surfaces*	15 minute dwell 24 hour dwell	68 oz/in (75/100 mm) 80 oz/in (88 N/100 mm)
- Polyethylene	15 minute dwell 24 hour dwell	52 oz/in (58 N/100 mm) 64 oz/in (70 N/100 mm)
Shear Adhesion To:	PSTC – 107	
- Stainless Steel	½" x ½" x 1000g	1 hours
Tack	PSTC – 6  Rolling Ball Tack	<2 inches
Luminous Values	DIN 67510 / ASTM 2072 (Xe lamp 1000Lx / 5 min) 10 min (Xe lamp 1000Lx / 5 min) 60 min	56 mcd/m <sup>2</sup> 7 mcd/m <sup>2</sup>
Coefficient of Friction (Kinetic)	ASTM D1894	

# NS5600B ANTI SLIP MOP FRIENDLY SAFETY GRIT TAPE

## PROPERTIES (continued)

PHYSICAL PROPERTIES	TEST METHODS	TYPICAL RESULTS
(Kinetic)	- Dry Rubber - Wet Rubber - Dry Leather - Wet Leather	0.7 0.7 0.7 0.8
Service Temperature		
- High	14 days at 150°F	No Visible Effects
- Low	14 days at -20°F	No Visible Effect

CHEMICAL PROPERTIES	REAGENT	RECOMMENDATIONS
Solvent Resistance (Product laminated to stainless steel panel and allowed to condition for 24 hrs at room temperature before testing. Sample was covered with reagent to the point that edges of product are also exposed to the reagent. This product is exposed to reagent for 1 hour at room temperature then reagent is removed and product is immediately tested for scrape resistances, delaminating and other visual effects.)	Water 10% Salt Water Bleach Trichloroethylene 25% Sulfuric Acid 1% Sodium Hydroxide Unleaded Gasoline Diesel Fuel Hydraulic Fluid 50% Antifreeze in water MEK Mineral Spirits 99% IPA	Recommended Recommended Recommended Not Recommended Intermittent Contact Only Recommended Recommended Recommended Recommended Recommended Recommended Intermittent Contact Only Recommended

- *Color and lot variances of coated surfaces including paints, powder coatings, lacquers, stains and other treatments may vary the performance of the tape and should be evaluated for the compatibility of the tape to the specific surface.*

**Note:** While the data contained herein is believed to be reliable averages of the product's properties, the data should not be used for specification purposes. Customers who desire specific performance data should contact No Skidding® Products for further recommendations.

### WARRANTY

The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representations, guarantees or warranties of any kind are made to the accuracy or suitability for specific applications.

### PLEASE READ AND FULLY UNDERSTAND LABEL AND MSDS BEFORE USING.

**Important:** Seller's and manufacturers only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for the intended use, and the user assumes all risk and liability whatsoever in connection therewith. No statement of recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of the seller and manufacturer. Buyer assumes all risk and liability associated with disposal.

**No Skidding® products are in use around the world in hotels, warehouses, factories, shopping malls, public transit systems, airports, hospitals and senior care, office complexes, restaurants, day care, schools, fitness clubs, government and military facilities.**

**The most complete range of slip injury prevention products in the World.**



266 Wildcat Rd, Toronto, ON M3J 2N5 Canada  
 Phone: (416) 667-1788 Fax: (416) 667-1783  
 sales@noskidding.com www.noskidding.com  
 or call us Toll Free at 1-800-375-0571

**We warehouse within the U.S. for our U.S. customers**  
 \* No Skidding® is a registered trademark of No Skidding Products, Inc., Toronto Canada