



PRODUCT DESCRIPTION

Liner: 80 lb super-calendered, silicone release treated on both sides

Adhesive: Acrylic

APPLICATIONS

- Laminating: paper, felt, sponge rubber, foam, and plastic
- Mounting: nameplates, decals, and plastic trim
- Weather stripping and gasket assembly

FEATURES AND BENEFITS

- Excellent anchorage to ether or ester foams, EPDM sponge, and plastics including PE, TPO, ABS, and PP
- Humidity and plasticizer migration resistance
- Excellent performance over a wide temperature range
- Durability under stress

PHYSICAL PROPERTIES

	Standard UOM	Metric UOM	Test Method
Adhesive Thickness	5.0 mils	127 microns	PSTC 133
Liner Thickness	4.5 mils	114 microns	PSTC 133
Adhesion Steel	130 oz/in	1417 N/m	PSTC 101 Mod
Shear Strength	> 24 hours		PSTC 107
Application Temperature	50°F to 150°F	10°C to 65°C	
Maximum Continuous Use	200°F	93°C	
Intermittent Use	250°F	121°C	

Recommended Storage Conditions: 40-60% Humidity, 60°F - 80°F

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.