



## PRODUCT DESCRIPTION

<b>Liner:</b>	80 lb super-calendered, silicone release treated on both sides
<b>Adhesive:</b>	Acrylic

## APPLICATIONS

- Laminating: paper, felt, sponge rubber, and plastic
- Mounting: nameplates, decals, and escutcheons

## FEATURES AND BENEFITS

- High tack adhesive with excellent adhesion to a variety of substrates
- Superior plasticizer migration resistance

## PHYSICAL PROPERTIES

	Standard UOM	Metric UOM	Test Method
Adhesive Thickness	2.0 mils	51 microns	PSTC 133
Liner Thickness	4.8 mils	122 microns	PSTC 133
Adhesion Steel	46 oz/in	501 N/m	PSTC 101 Mod
Shear Strength	168+ hours		PSTC 107
Application Temperature	32°F to 180°F	0°C to 82°C	
Laminating Temperature	60°F to 250°F	16°C to 121°C	
Maximum Continuous Use	200°F	93°C	
Intermittent Use	250°F	121°C	

Recommended Storage Conditions: 40-60% Humidity, 60°F - 80°F

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.