



### PRODUCT DESCRIPTION

**Liner:** Kraft Liner: 60 lb or 80 lb  
Board: 8 pt or 12 pt

**Adhesive:** Rubber

### APPLICATIONS

- Laminating: paper, felt, sponge rubber, foam and plastic
- High peel bonding and assembly

### FEATURES AND BENEFITS

- Designed for applications requiring high peel strength
- Bonds well to most polyurethane ether and ester foams, closed and open cell sponge rubber, and most metal and plastic surfaces
- Available on different liners. The liner options are a 60 lb or 80 lb kraft liner or an 8 pt or 12 pt board

### PHYSICAL PROPERTIES

	Standard UOM	Metric UOM	Test Method
Adhesive Thickness	2.0 mils	51 microns	PSTC 133
Liner Thickness	4.6 mils	117 microns	PSTC 133
Adhesion Steel	120 oz/in	1308 N/m	PSTC 101 Mod
Application Temperature	50°F to 150°F	10°C to 65°C	
Operating Temperature	-30°F to 190°F	-34°C to 88°C	

*Liner thickness is for the 80 lb liner*

Recommended Storage Conditions: 40-60% Humidity, 60°F - 80°F

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.