



PRODUCT DESCRIPTION

Liner:	60 lb bleached kraft, silicone release treated on both sides
Liner Side Adhesive:	Rubber
Carrier:	0.5 mil polyester film
Air Side Adhesive:	Rubber

APPLICATIONS

- Mounting: nameplates, decals, escutcheons
- Bonding and Assembly: foam and plastics

FEATURES AND BENEFITS

- Good adhesion to PE foams and low surface energy substrates
- Medium peel and shear with high tack performance

PHYSICAL PROPERTIES

	Standard UOM	Metric UOM	Test Method
Adhesive Thickness (Air Side)	1.2 mils	30 microns	PSTC 133
Adhesive Thickness (Liner Side)	1.2 mils	30 microns	PSTC 133
Carrier Thickness	0.5 mils	13 microns	PSTC 133
Liner Thickness	3.5 mils	89 microns	PSTC 133
Adhesion Steel (Air Side)	64 oz/in	698 N/m	PSTC 101 Mod
Adhesion Steel (Liner Side)	64 oz/in	698 N/m	PSTC 101 Mod
Shear Strength (Air Side)	24+ hours		PSTC 107
Shear Strength (Liner Side)	24+ hours		PSTC 107
Application Temperature	40°F to 150°F	4°C to 65°C	
Laminating Temperature	68°F to 225°F	20°C to 107°C	
Maximum Continuous Use	160°F	71°C	
Intermittent Use	180°F	82°C	

Recommended Storage Conditions: 40-60% Humidity, 60°F - 80°F

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.